

Anisotropic relaxivity measurements of solubilized multiwall carbon nanotubes suspensions reveal molecular orientation.

Daniel Calle¹, Viviana Negri², Arisbel Cerpa³, Pilar López-Larrubia¹, Paloma Ballesteros², and Sebastián Cerdán¹

¹Departamento de Modelos Experimentales Humanos, Instituto de Investigaciones Biomédicas "Alberto Sols", CSIC, Madrid, Madrid, Spain, ²Laboratory of Organic Synthesis and Molecular Imaging by Magnetic Resonance, Faculty of Sciences, UNED, Madrid, Madrid, Spain, ³Universidad Europea de Madrid, Madrid, Madrid, Spain

Introduction. Magnetic Resonance Image contrast is normally obtained using Gd(III) paramagnetic complexes or superparamagnetic nanoparticles, which reduce the T_1 or T_2 values of the water molecules located in the tissues where they accumulate. Gd(III) complexes and superparamagnetic particles rotate fast in the NMR time scale averaging spherically their relaxivity values. Under these conditions, water relaxation induced by classical contrast agents occurs isotropically, becoming not possible to determine the orientation of the contrast agent probe from relaxivity measurements. In this work we aimed to investigate novel contrast agents with anisotropic relaxivity (1,2). Multi Walled Carbon Nanotubes (MWCNTs) are potentially useful systems for this purpose since they align with magnetic field and depict different magnetic properties in the longitudinal and axial directions, preserving anisotropic relaxivity in the NMR timescale (Fig1A). Here we report the first measurements to our knowledge of directional relaxivity of MWCNTs suspensions fixed in agarose gels.

Materials and Methods. We used commercial MWCNTs (SES Research, Houston, TX, USA), <10 nm diameter, 1-5 micron average length. It was proven that the preparation of MWCNTs depicted magnetic moment since it was possible to move the preparation along an Eppendorff tube with an external magnet. They were oxidized by sulfonitric acid (3) and, subsequently, they were treated with 1-AminoPyrene (in dimethylformamide) to obtain soluble adducts by π - π stacking interactions. Finally, the solution (0.03mg/mL) was: mixed with melted agarose (0.5%, low melting 37°C, Sigma-Aldrich, St. Louis, Mo, USA), and cooled down (22°C) to form a solid gel inside a 7T magnet. This protocol was able to maintain oriented the MWCNTs in the B_0 direction while gelling, keeping this orientation in the solid agarose matrix thereafter. The MWNTs oriented sample was placed in an Eppendorff tube accommodated to a home made PVC goniometer, allowing the rotation of the sample inside the magnet. We measured T_1 and T_2 values varying the orientation of the sample with respect to B_0 . We used a progressive saturation or gradient echo sequences as implemented in a Bruker Pharmascan 7 Tesla scanner (Bruker Daltonics, Ettlingen, DE), employing a 38 mm volume coil.

Results. It was possible to demonstrate significant different values of T_1 and T_2 when measured under parallel or perpendicular orientations to B_0 (Figures 1B and 1C).




Figure 1. A: Spherical nanoparticles depict isotropic magnetic susceptibility while MWCNTs depict larger magnetic susceptibility along the longitudinal axis of the nanotube. B: Representative T_1 (I - II) and T_2 maps (III - IV) from oriented MWCNTs in agarose. I and III or II and IV maps, correspond to parallel or perpendicular orientations with respect to B_0 , respectively. Note the different values in the two orientations. C: T_1 and T_2 values of water (mean \pm sd) from an oriented MWCNTs suspension in solid agarose-, in the parallel and perpendicular orientations to the B_0 field. Both results are statistically significant ($p < 0.01$).

Fig. 1C shows the variation of T_1 and T_2 varying the orientation of the nanotubes with respect to the static magnetic field B_0 . A significant decrease is observed when the nanotube suspension is oriented perpendicular to the magnetic field B_0 . This response reflects a differential susceptibility effect, increasing the local magnetic field in the top and bottom extremes of the nanotube and decreasing it in the sidewalls. The variation detected is yet small probably due to the small concentration of MWCNTs and their reduced magnetic susceptibility at room temperature under the conditions of our study.

Conclusions. We show that oriented MWCNTs depict anisotropic relaxivity in T_1 and T_2 , a property that may allow to unravel the molecular orientation of the probe from relaxivity measurements. In addition, we report a convenient method to obtain magnetically oriented MWCNTs suspensions, able to maintain the orientation within a solid agarose matrix. By changing the orientation of the agarose matrix inside the magnet with a home made, manual goniometer, we were able to prove the directional dependence of relaxivity in the MWCNTs suspension.

Bibliography.

- (1) V. Negri, A. Cerpa, P. López-Larrubia, L. Nieto-Charques, S. Cerdán, P. Ballesteros. Nanotubular Paramagnetic Probes as Contrast Agents for Magnetic Resonance Imaging Based on the Diffusion Tensor. *Angewandte Chemie* 2010, 49: 1813-1815.
- (2) J. Tumpene, N. Karousis, N. Tagmatarchis, B. Nordén. Alignment of Carbon Nanotubes in Weak Magnetic Fields. *Angewandte Chemie* 2008, 47: 5148-5152.
- (3) C. Samori, R. Sainz, C. Ménard-Moyon, F. Toma, E. Venturelli, P. Singh, M. Ballestri, M. Prato, A. Bianco. Potentiometric titration as a straightforward method to assess the number of functional groups on thosrtened carbon nanotubes. *Carbon* 2010, 48: 2447-2454.